

C R

CR N 572

General:

CR, black, high-grade Sulphur crosslinked Resistant to most aliphatic oils Non resistant against aromatic oils Self-extinguishing according to ISO 4580-2: 2017, O₂ Index up to 30% (depending on the thickness and the shape of the specimen)

Wrapping: stretched foil, labelled standard finishing in separation foil

*SVHC-free

Working temperature range

Medium	dyn.(stat.)	max.	short-term
Air	-20 (-40)°C	+90°C	+120°C
Water		+70°C	+90°C
oil		+80°C	+100°C

Compression set DIN ISO 815

Duration	Temperature	CS
22h	+70°C	35%

Ageing ISO 188

Conditions	Hardness	Strength	Elongation
70h / 70°C	5 Shore A	5 %	15 %

Swelling ISO 1817

Medium	Conditions	Hardness	Volume
IRM 901	70h / 100°C	5 Shore A	10 %

ROTACURED SHEETS product number	Thickness mm	Width mm	Length mm
401126100	1,0	1.400	20.000
401126150	1,5	1.400	20.000
401126200	2,0	1.400	20.000
401126300	3,0	1.400	10.000
401126400	4,0	1.400	10.000
401126500	5,0	1.400	10.000
401126600	6,0	1.400	10.000
401126800	8,0	1.400	5.000
401126000	10,0	1.400	5.000

PAH disclaimer:

Referring to an international proficiency test and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate:

* Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit are only accurate to approx. ± 70%.

* Results of the overall limit of < 50 mg/kg are only accurate to approx. $\pm\,35\%$

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

Properties:

Hardness [Shore A]:	ISO 7619-1	70±5		
Density [g/cm ³]:	ISO 1183-1	~1,55		
Tensile Strength [N/mm ²]:	ISO 37 type 2	7		
Elongation at Break [%]:	ISO 37 type 2	300		
correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics				
of Elastomer sheets and plates	33			

Stabilities:

Ozone resistance: Weather resistance: Oil resistance: Fuel resistance: (only alcohol-free fuels!) Acid resistance: Strong bases: Abrasion resistance: resistant good resistant resistant – no aromatic oils moderately resistant

resistant resistant moderately resistant

ROTACURED SHEETS product number	Thickness mm	Width mm	Length mm
421326120	12,0	1.400	5.000
421326150	15,0	1.400	5.000
421326200	20,0	1.400	5.000
421326250	25,0	1.400	5.000
421326300	30,0	1.400	5.000
421326400	40,0	1.400	5.000

Please note:

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualitied engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions, available on our website or on request. ©Copyright 2020 Semperit Technische Produkte GmbH

Subject to alteration without prior notice: In order to always have the latest product- and safety information make sure you visit our website (<u>www.semperitgroup.com</u>) regularly or contact specialist dealers or a Semperit application engineer. Additional important general information about the range, storage and tolerances can also be found at our website (<u>www.semperitgroup.com</u>) and must be followed without exception.

SEMPERIT (S)