SEMPERIT S

D70 A 608

NR-SBR, grey - commercial

 matting with hammerblow surface (one side hammerblow design, one side fabric impression)

S packaging see General Information

Hardness [Shore A]: 70 ± 5 Density [g/cm³]: 1.60Tensile strength [N/mm²]: 5Elongation at break [%]: 300

Ozone resistance: resistant Weather resistance: resistant

Oil resistance: moderately resistant

Benzine resistance: non resistant

Acid resistance: moderately resistant

Strong bases: resistant

Abrasion resistance: moderately suitable

WORKING	TEMPERATURI	E RANGE	
Medium	dvn. (stat.)	max.	

 fledium
 dyn. (stat.)
 max.
 short-term

 Air
 (-20) °C
 +70 °C
 +90 °C


COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	50 %

Gumex ... pruzne partnerstv

ROTA-CURED-SHEETS

KOTA CORED CHEETO								
	Article-	Thickness	Width	Length	No. of			
	number	mm	m	m	insert.			
	4024 99063	3.0	1.4	10	0			
	4024 99064	3.0	1 25	10	0			



Please Note:

22.8.2003

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.

Subject to alteration without prior notice - All mentioned properties contained in this catalogue are guiding values representing longterm experience average.

Semperit Technische Produkte Gesellschaft m.b.H. & Co KG A-2632 Wimpassing, Triester Bundesstraße 26 Telefon +43 2630 310-0*, Telefax +43 2630 310 320 E-Mail: semperflex@semperit.at, Internet: www.semperit.at

