

GRABO

1905

20 JSK

Technical datasheet

COMMERCIAL

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	2
Wear layer thickness	EN ISO 24340	mm	0,9
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m2	2,4
CLASSIFICATION			
European classification	EN 685	class	34/43
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	0,2
Fire resistance	EN 13501-1	class	Bfl-s1
	BS 476		Class 1
	DIN 4102/ÖNORM	class	B1
	Gost 30402-94		G1
Slip resistance	DIN 51130		R10
	DIN 51097		C
	EN 13893	class	DS
Abrasion resistance	ISO 9352	g/1000 circle	-0,25
Shore A hardness	ISO 868		90
Chemical resistance	EN ISO 26987		✓
Light fastness	EN 20105 B02	grade	6
Castor chair resistance	EN ISO 4918		✓
Surface treatment			CLP
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Phthalate, Solvent and Heavy metal free product
Seaming method			heat or cold weld
Warranty		year	10
CE MARKING	EN 14041		✓

GRABOPLAST Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
info@grabo1905.com www.grabo1905.com